



Everest Roof Base Coat – Data Sheet

Description:

Everest Roof Base Coat is a Hi-Build modified acrylic formulated specifically for use as the bond coat for re-chipping Decromastic roof tiles.

Physical Properties

Resin Type:	Modified Acrylic emulsion
Solvent:	Water
Colour:	White and standard roof colours
Finish:	N/A
Drying time:	2 hours at 18°C
Recoat time:	3 hours at 18°C
Dry Film Thickness:	150µ minimum
No. of coats:	2
Theoretical Coverage:	3m ² /litre to attain 150µ DFT.
Primer Needed:	No
Thinning & Cleaning:	Water

Performance:

- Excellent adhesion to substrate.
- High cohesive bond strength for adhering roofing chip and finish coat.
- Very good flexibility

Limitations:

- Do not apply when temperature is below or expected to fall under 10°C.
- Requires at least 1 finish coat of **Everest Roof Paint**.
- Should not be used in areas of ponding water.

Substrate Preparation:

Ensure all surfaces are clean and dust free. All loose chip should be removed. If mould and fungus is present use **Everest Moss & Mould Kill**. Water blasting at 3000psi is the recommended method of surface preparation

Application:

Everest Roof Base Coat(concrete tiles) is part of a system. Please refer to Paint Tech Paint Supplies Ltd for specific information on usage and application.

Everest Colour Prime Roof Primer(where higher adhesion is required) is part of a system. Please refer to Commercial Coating Manufactures Ltd for specific information on usage and application.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof.

In no event will Commercial Coating Manufactures Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.

Commercial Coating Manufacturers Ltd:
PO Box 33529 Takapuna
Auckland 0740, New Zealand
(09)4122983
(029)4114309

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof.
In no event will Commercial Coating Manufactures Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.