



THE PEAK OF PAINT PERFORMANCE

Subflex 1000 – Data Sheet

Description:

Subflex 1000 is water based Hi-Build Acrylic finish coat for exterior surfaces. Its unique formulation imparts a high degree of water resistance and elastomeric properties making it an ideal final finish over cementitious substrates, concrete blocks and EIFS. The elastomeric properties of Subflex 1000 will help minimize water ingress resulting from small substrate surface cracking.

Physical Properties

Resin Type	Acrylic Emulsion
Solvent	Water
Colour	White & Pastels. Dark Colours made to order
Finish	Silk
Drying time	1 hour at 18°C
Recoat time	3 hours
Dry Film Thickness	200µ minimum
No. of coats	2 minimum to attain 200µ
Theoretical Coverage	4-5m ² per litre per coat to attain DFT of 200µ
Primer Needed	Yes, depending on substrate
Thinning & Cleaning	Does not require thinning, wash up with water.

Performance:

- Very good exterior durability, does not need finishing coat.
- Excellent crack filling properties.
- Very easy to apply.
- Minimizes mould and fungal growth.

Limitations:

- Do not apply at temperatures less than 10°C or when temperature will fall below 10°C during the drying time.
- Not formulated for ponding water
- Weathered concrete needs to be sealed with **Everest-Tech Sealer**

Substrate Preparation:

Ensure all surfaces are clean and dust free. If mould and fungus use **Everest Moss & Mould Kill**. Water blasting at 3000psi is the recommend method of surface preparation. When surface is clean and dry, use the following primers and sealers.

Glossy Concrete	Use Everest Tech Sealer
New Cementitious surfaces	Use Everest Lime Seal
Concrete Blocks	May be applied without priming if surface is clean and free from dirt and friable dust.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof.

In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.

Application:

Subflex 1000 may be applied by standard and airless spray, brush and roller. Ensure that 2 coats are applied at the specified rate.

NB: To ensure complete water resistance on concrete blocks a 3rd coat is recommended. This is to overcome possible regional differences in the quality of the blocks.

Commercial Coating Manufacturers Ltd:
PO Box 33529 Takapuna
Auckland 0740, New Zealand
(09)4122983
(029)4114309

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Commercial Coating Manufacturers Ltd makes no representation as to the completeness and accuracy thereof.
In no event will Commercial Coating Manufacturers Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.